

# Technical data sheet



## Compound EL R401/60 + E

Typical general characteristics	Inspection Method	Value
<b>Cure</b>	10 min / 135°C	
<b>Post-cure</b>	4 h / 200°C	
Appearance		transparent
Density at 20 °C	ISO 1183-1 A	approx. 1,15 g/cm <sup>3</sup>
<b>Curing agent E</b>		
Hardness Shore A	DIN 53505	61
Tensile strength	DIN 53504 S1 / ISO 37	11,00 N/mm <sup>2</sup>
Elongation at break	DIN 53504 S 1	440 %
Tear strength	ASTM D 624 B	24 N/mm
Rebound resilience	DIN 53512	57 %
Compression set	DIN ISO 815-B (22 h / 175 °C)	31 %

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.