

Data Sheet

Rubber compound **RSN65155** Base of NR/SBR rubber

name materiál:	NR/SBR compound
Type of materiál:	Rubber compound on base NR/SBR
Elastomer:	NR / SBR
Color:	Black
Storage life min. days	60
Delivery form:	Stripes 350x5mm wig-wag, 1.000 kg / palet

	Value	Unit	Standard
Density	1,1 – 1,2	g/cm 3	DIN 53497
Hardness	60 ± 5	Shore A	DIN 53505
Tensile strength	Min. 14	MPa	DIN 53504
Elongation at break	Min. 350	%	
Abrasion	Max 115	mm ³	
Mooney viscosity 100°C	45-55	ML	



Press conditions: 150°C/20'

Vulkanized cure: 150°C/20'

ML dNm 2,5

MH dNm 16,3

Ts2 min 1,33

T 90 min 3,35